

Specifications for SS1H Conforms to ASTM D 977

ANIONIC ASPHALT EMULSION (SOLVENT FREE) COMMONLY
USED FOR TACK COAT, FOG SEAL, A BINDER FOR AGGREGATE
FILLED SYSTEMS AND WATERPROFFING

<u>TEST</u>	<u>METHOD</u>	<u>RANGE</u>
Penetration of Residue	ASTM D5977	40-60
Solids/Residue by Evap.	ASTM D2939-98	60-63%
pH	Test with meter	10.6-11.2
Sieve	ASTM D244	pass <0.20%
Viscosity	ASTM D1417 (Brookfield 77F)	100-200 cps
Settlement, 7 days, %	Observation/Weight	3 max
Miscibility with water	3 to 1 dilution, 2 hours	Pass

NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE, ARE MADE WITH RESPECT TO THE PRODUCTS DESCRIBED HEREIN.

